

# PATENT ABSTRACTS OF JAPAN

(11)Publication number : 11-273861

(43)Date of publication of application : 08.10.1999

(51)Int.Cl.

H05B 33/14

C09K 11/06

C09K 11/06

(21)Application number : 10-076041

(71)Applicant : ASAHI GLASS CO LTD

(22)Date of filing : 24.03.1998


(72)Inventor : TERASONO SHINJI  
ASARI GORO  
TAKAHASHI AKIRA

## (54) ORGANIC ELECTROLUMINESCENT ELEMENT


### (57)Abstract:

**PROBLEM TO BE SOLVED:** To improve luminous efficiency and realize stable light emission over a long term by including a predetermined quantity of one or more compounds from among 9, 10-diphenylanthracene and rubrene compounds in a luminescent layer.

**SOLUTION:** One or more compounds of 0.01-30 mol.% selected from among a group comprising 9,10-diphenylanthracene compounds expressed by formula I and rubrene compounds expressed by formula II are included in a luminescent layer. In the formula I and II, R<sup>1</sup>-R<sup>20</sup> each independently represents a hydrogen atom, halogen atom, alkyl group, alkoxy group, aryl group, aryloxy group, acyl group or aralkyl group. A part of hydrogen atoms of these groups may be replaced by halogen atoms, and an oxygen atom may be inserted in between carbon-carbon combination. By using those compounds, voltage rise and luminescence degradation can be suppressed in the continuous driving of a luminescent layer using an 8-hydroxyquinoline complex.



I



II

## LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted to registration]

[Date of final disposal for application]

[Patent number]